

Designazione Attuale		Vecchie Designazioni								
EN 10025-2:2004		EN 10025:1990 A1:1993		EN 10025:1990	Italia UNI 7070	Germania DIN 17 100	Francia NF A 35-501	GB BS 4360	Spagna UNE 36-080	USA ASTM
		Impiego Strutturale								
		S235JR	1.0037	Fe 360 B	Fe 360 B	St 37-2	E 24-2			A283(A/B/C/D)
		S235JRG1	1.0036	Fe 360 BFU		USt 37-2			AE 235 BFU	
S235JR	1.0038	S235JRG2	1.0038	Fe 360 BFN		RSt 37-2		40 B	AE 235 BFN	A284 gr/C/D
S235JO	1.0114	S235JO	1.0114	Fe 360 C	Fe 360 C	St 37-3 U	E 24-3	40 C	AE 235 C	
	1.0116	S235J2G3	1.0116	Fe 360 D1	Fe 360 D	St 37-3 N	E 24-4	40 D	AE 235 D	
S235J2	1.0117	S235J2G4	1.0117	Fe 360 D2						A 36
S275JR	1.0044	S275JR	1.0044	Fe 430 B	Fe 430 B	ST 44-2	E 28-2	43 B	AE 275B	A 529 gr 42,50
S275JO	1.0143	S275JO	1.0143	Fe 430 C	Fe 430 C	ST 44-3 U	E 28-3	43 C	AE 275C	
		S275J2G3	1.0144	Fe 430 D1	Fe 430 D	ST 44-3 N	E 28-4	43 D	AE 275D	A 572 gr 42,50
S275J2	1.0145	S275J2G4	1.0145	Fe 430 D2						
S355JR	1.0045	S355JR	1.0045	Fe 510 B	Fe 510 B		E 36-2	50 B	AE 355 B	A 633

Designazione Attuale		Vecchie Designazioni								
EN 10025-2:2004		EN 10025:1990 A1:1993		EN 10025:1990	Italia UNI 7070	Germania DIN 17 100	Francia NF A 35-501	GB BS 4360	Spagna UNE 36-080	USA ASTM
S355JO	1.0553	S355JO	1.0553	Fe 510 C	Fe 510 C	St 52-3U	E 36-3	50 C	AE 355 C	gr A/C/D
		S355J2G3	1.0570	Fe 510 D1	Fe 510 D	St 52-3N		50 D	AE 355 D	
S355J2	1.0577	S355J2G4	1.0577	Fe 510 D2						A 656 g 50
		S355K2G3	1.0595	Fe 510 DD1			E 36-4	50 DD		
S355K2	1.0596	S355K2G4	1.0596	Fe 510 DD2						
SJ450JO	1.0590							55 C		
Costruzioni Meccaniche										
E295	1.0050	E295	1.0050	Fe 490-2	Fe 490	St 50-2	A 50-2		A 490	
E355	1.0060	E355	1.0060	Fe 590-2	Fe 590	St 60-2	A 60-2		A 590	
E360	1.0070	E360	1.0070	Fe 690-2	Fe 690	St 70-2	A 70-2		A 690	
Laminati a Freddo										
EN 10027-2		EN 10027-1	EN 10027-2		UNI 5866	DIN 1623	NF A 36 401	BS 1449		ASTM
1.0330		DC01	1.0330		Fe P01	St12		CR SP4		A 366.85

Designazione Attuale		Vecchie Designazioni								
EN 10025-2:2004		EN 10025:1990 A1:1993		EN 10025:1990	Italia UNI 7070	Germania DIN 17 100	Francia NF A 35-501	GB BS 4360	Spagna UNE 36-080	USA ASTM
		Laminati a Caldo								
EN 10027-2		EN 10111	EN 10027-2		UNI 5866	DIN 1623	NF A 36 301	BS 1449		ASTM
					Fe P10		0C	HR4		
1.0332		DD11	1.0332		Fe P11	StW 22	1C	HR3		A569 CQ
1.0398		DD12	1.0398		Fe P12	StW 23	2C	HR2		A569 DQ
1.0335		DD13	1.0335		Fe P13	StW 24	3C	HR1K		A622 DQAK